






9Glens® Medical Ltd

Viscoelastic Solutions

Superior Quality Cohesive OVD / Made in Germany

- Good maintenance of the anterior chamber and the capsular bag
- Controlled capsulorhexis
- Easy implantation
- Better adhesiveness on the corneal endothelium during phacoemulsification
- Favorable environment for ophthalmic surgery
- Excellent protection against mechanical damages
- Steam sterilized
- No refrigeration necessary
- Shelf life 42 months

9G-Visc 1.0%	Technical Specification	Formula, each ml contains:
	Sodium Hyaluronate 1.0% Molecular Weight 1.1 - 1.5 Million Daltons Viscosity approx. 30,000 mPas Osmolality 270 - 400 mOsm/kg Storage 2 - 25°C pH 6.8 - 7.4 Volume 1.0 ml	Sodium Hyaluronate 10.000 mg Sodium Chloride 8.500 mg Disodium Hydrogenphosphate 0.563 mg Sodium Dihydrogenphosphate 0.045 mg Water for injection q.s. One syringe contains 1 ml of solution Sterilized by moist heat
9G-Visc 1.4%	Technical Specification	Formula, each ml contains:
	Sodium Hyaluronate 1.4% Molecular Weight 1.1 - 2.0 Million Daltons Viscosity 20,000 - 60,000 mPas Osmolality 270 - 400 mOsm/kg Storage 2 - 25°C pH 6.8 - 7.4 Volume 1.0 ml	Sodium Hyaluronate 14.000 mg Sodium Chloride 8.500 mg Disodium Hydrogenphosphate 0.563 mg Sodium Dihydrogenphosphate 0.045 mg Water for injection q.s. One syringe contains 1 ml of solution Sterilized by moist heat
9G-Visc 1.6%	Technical Specification	Formula, each ml contains:
	Sodium Hyaluronate 1.6% Molecular Weight 1.3 - 2.0 Million Daltons Viscosity 20,000 - 80,000 mPas Osmolality 270 - 400 mOsm/kg Storage 2 - 25°C pH 6.8 - 7.4 Volume 1.0 ml	Sodium Hyaluronate 16.000 mg Sodium Chloride 8.500 mg Disodium Hydrogenphosphate 0.563 mg Sodium Dihydrogenphosphate 0.045 mg Water for injection q.s. One syringe contains 1 ml of solution Sterilized by moist heat
9G-Visc 1.8%	Technical Specification	Formula, each ml contains:
	Sodium Hyaluronate 1.8% Molecular Weight 1.2 - 2.0 Million Daltons Viscosity 50,000 - 130,000 mPas Osmolality 270 - 400 mOsm/kg Storage 2 - 25°C pH 6.8 - 7.4 Volume 1.0 ml	Sodium Hyaluronate 18.000 mg Sodium Chloride 8.500 mg Disodium Hydrogenphosphate 0.563 mg Sodium Dihydrogenphosphate 0.045 mg Water for injection q.s. One syringe contains 1 ml of solution Sterilized by moist heat
9G-Visc 3.0%	Technical Specification	Formula, each ml contains:
	Sodium Hyaluronate 3.0% Molecular Weight 1.0 - 1.8 Million Daltons Viscosity 120,000 - 300,000 mPas Osmolality 270 - 400 mOsm/kg Storage 2 - 25°C pH 6.8 - 7.4 Volume 1.0 ml	Sodium Hyaluronate 30.000 mg Sodium Chloride 8.500 mg Disodium Hydrogenphosphate 0.563 mg Sodium Dihydrogenphosphate 0.045 mg Water for injection q.s. One syringe contains 1 ml of solution Sterilized by moist heat

Manufacturer:



9Glens® Medical Ltd
 Oberndorferstr. 72
 D-64347 Griesheim / Germany
 www.9glensmedical.com

Phone +49 (0)6155 - 82 58 43
 Fax +49 (0)6155 - 82 82 89
 info@9glensmedical.com

Distributed by:

